

Technical data sheet

PETP-SP

General properties				
Material designation	PETP-SP			
Material colour(s)	light gray			
Raw material	PET Polyethylene terephthalate			
Molecular weight (Average molar mass)	-			
Mechanical properties		Unit	Test method	Value
Density	g/cm ³	DIN EN ISO 1183	1,43	
Tensile strength	MPa	DIN EN ISO 527	65	
Shore D hardness, 15s - Value	Skala D	DIN EN ISO 868	-	
Ball indentation hardness, 30s - Value	MPa	DIN ISO 2039 Teil 1	128	
Ultimate tensile strength	MPa	DIN EN ISO 527	75	
Elongation at break	%	DIN EN ISO 527	5	
Modulus of elasticity	MPa	DIN EN ISO 527	2.200	
Notched impact strength (Charpy)	kJ/m ²	DIN EN ISO 179	2	
Wear resistance	%	Sand Slurry method	-	
Coefficient of friction (to steel)	μ		0,2	
Thermal properties		Unit	Test method	Value
Dimensional stability under heat	°C	DIN 53461	75	
Vicat softening temperature	°C	DIN EN ISO 306	-	
Crystalline melting range	°C	DIN EN ISO 11357	255	
Thermal conductivity at 23°C	W/ (K * m)	DIN 52612	0,23	
Specific heat at 23°C	kJ / (K * Kg)		1,5	
Coefficient of linear expansion at 23°C	10 ⁻⁵ * (1/K)	DIN ISO 11359	8	
Fire behaviour		UL 94	HB	
Application temperature (min.)	°C		- 20	
Application temperature (constant)	°C		+ 110	
Moisture absorption	%		0,2	
Electrical properties		Unit	Test method	Value
Specific volume resistance	Ω * cm	IEC 60093	10 ¹⁶	
Specific surface resistance	Ω	IEC 60093	10 ¹⁴	
Dielectric strength	KV/mm	IEC 60243	-	
Conformity with food secure regulations				
FDA	Conforms to FDA regulations			
EU	EU 1935/2004 - EU 10/2011 [FSP quality]			

Our employees are available to answer all of your questions.

You can find additional information on our material qualities on the internet at www.wefapress.com/en/materials.

All stated information reflects our current knowledge. No agreement or guarantee regarding specific characteristics can be derived from the information contained in the datasheets. Each user is responsible for deciding on the suitability of a material for a specific purpose. The data supplied are subject to change.

The materials labelled as a "Food Secure Product" (FSP) comply with the provisions of Regulations (EU) No. 10/2011 and No. 1935/2004.